Machining with AlCr-oxinitride PVD coated cutting tools

Pilkington, Antony; Dowey, Steve; Toton, Jimmy; Doyle, Edward

https://researchrepository.rmit.edu.au/esploro/outputs/9921859348901341/filesAndLinks?institution=61RMIT_INST&index=null

Pilkington, A., Dowey, S., Toton, J., & Doyle, E. (2013). Machining with AlCr-oxinitride PVD coated cutting tools. *Tribology International*, 65, 303–313. <https://doi.org/10.1016/j.triboint.2013.03.020>
Document Version: Accepted Manuscript

Published Version: <https://doi.org/10.1016/j.triboint.2013.03.020>

Thank you for downloading this document from the RMIT Research Repository.

The RMIT Research Repository is an open access database showcasing the research outputs of RMIT University researchers.

RMIT Research Repository: <http://researchbank.rmit.edu.au/>

Citation:

Pilkington, A, Dowey, S, Toton, J and Doyle, E 2013, 'Machining with AlCr-oxinitride PVD coated cutting tools', *Tribology International*, vol. 65, pp. 303-313.

See this record in the RMIT Research Repository at:

<https://researchbank.rmit.edu.au/view/rmit:23357>

Version: Accepted Manuscript

Copyright Statement: © 2013 Elsevier Ltd.

Link to Published Version:

<http://dx.doi.org/10.1016/j.triboint.2013.03.020>

Manuscript Number:

Title: Machining with AlCr-Oxinitride PVD Coated Cutting Tools

Article Type: Leeds-Lyon 2012

Keywords: Machining; PVD coating; abrasive adhesive wear; AlCr oxy-nitride

Corresponding Author: Mr. Antony Pilkington, B.Eng., MSc.

Corresponding Author's Institution: RMIT University

First Author: Antony Pilkington, B.Eng., MSc.

Order of Authors: Antony Pilkington, B.Eng., MSc.; S J Dowey, B. Eng, PhD; J T Toton, BSc; E D Doyle, BSc., MSc., PhD

Abstract: Physical Vapour Deposition (PVD) coating materials based on transition metal oxy-nitrides have been found to offer improved oxidation resistance for tooling applications. Arc deposited AlCrOxN1-x coatings were tested on M2 HSS drills in drilling 2.5D holes in AISI D2. At a speed of 30 m/min and feed 0.025 mm/rev the mean tool life was 17.2 holes / μ m for coatings made with a N2/O2 ratio of 0.9/0.1. Coating deposition with a pulse bias of 10 kHz was found to improve tool life in the drilling test by 10% compared to DC bias coatings. In milling of stainless steel AlCrOxN1-x coated carbide end mills cutting AISI 316 at 70 m/min achieved a cut length 2.5X uncoated tools under the accelerated test conditions.

A. Pilkington
Department of Applied Physics
RMIT University
14-7-5a Swanston Street
Melbourne
Victoria 3000
Australia

11-9-2012

To: The editor, Tribology International

Research article: Machining with AlCr-Oxinitride PVD Coated Cutting Tools

Dear Sir

We have pleasure in submitting our paper to the Special Issue of the Proceedings of the 39th Leeds-Lyon Tribology Symposium. A shorter version of the paper was presented by Antony Pilkington at the conference in Session X as Paper V.

We report the results of practical machining studies of recently developed AlCr-oxinitride arc deposited PVD tool coatings. We present novelty in our coating design and manufacturing route which has not previously been reported in Tribology International. We have investigated the effects of oxygen incorporation and bias mode on the mechanical properties of AlCrN PVD coatings.

Accelerated tool life testing was carried using round shank engineering tooling representing different levels of technological advancement. In drilling tests M2 HSS jobber drills represented a tool of baseline technology and an end milling study used an advanced design of vary-index carbide end-mill with robust life enhancing features such as edge finishing and sub-micron carbide specification. The AlCr-oxinitride coatings were shown to provide abrasive wear protection to HSS drills and the drill test was able to discriminate between the different treatments. We benchmarked the drill life by normalising against the coating thickness to benchmark against AlCrN, the current state of the art PVD tool coating, in contrast to the more common and inappropriate use of TiN or uncoated HSS tooling.

The measurement of tool wear was carried out using an Infinite Focus Microscope (Alicona IFM) and this was found to be advantageous. The novel use of this optical microscopy technique is certain to be of wider interest to Tribology International readers since it represents an important advancement in the quantification of surfaces, micro-geometry and wear. The practical advantages demonstrated by IFM imaging are in accuracy, non-destructive measurement and capability to measure features on complex geometries. This instrument has become indispensable in the author's laboratory for measurement of manufactured tool surfaces and wear resulting in service so we are pleased to showcase the capabilities in this paper.

Yours faithfully

Tony Pilkington

On behalf of the authors

A. Pilkington^{*ab}, S.J. Dowey^{abc}, J.T. Toton^{ab} and E.D. Doyle^{ab}

^a Department of Physics, School of Applied Sciences, RMIT University, Swanston Street, Melbourne, VIC 3000, Australia

^b Defence Materials Technology Centre, Level 2 No.24 Wakefield Street, Hawthorn, VIC 3122, Australia

^c Sutton Tools Pty Ltd, 378 Settlement Road, Thomastown, VIC 3074, Australia

*Corresponding author: antony.pilkington@rmit.edu.au

The research work submitted under the title “**Machining with AlCr-Oxinitride PVD Coated Cutting Tools**”

Was conducted by the Defence Materials Research Centre^b and is the original work of the following authors:

A. Pilkington^{*ab}, S.J. Dowey^{abc}, J.T. Toton^{ab} and E.D. Doyle^{ab}

^a Department of Physics, School of Applied Sciences, RMIT University, Swanston Street, Melbourne, VIC 3000, Australia

^b Defence Materials Technology Centre, Level 2 No.24 Wakefield Street, Hawthorn, VIC 3122, Australia

^c Sutton Tools Pty Ltd, 378 Settlement Road, Thomastown, VIC 3074, Australia

*Corresponding author: antony.pilkington@rmit.edu.au

The work is not submitted for publication elsewhere in this form and has not been published previously in any other journal.

Antony Pilkington

11/9/2012

*Research Highlights

- $\text{AlCrO}_x\text{N}_{1-x}$ coatings were deposited by cathodic arc with DC and pulse bias
- M2 HSS drills coated with $\text{AlCrO}_x\text{N}_{1-x}$ had reduced lip wear in drilling AISI D2
- $\text{AlCrO}_x\text{N}_{1-x}$ coatings were more sensitive to O_2 content than to bias mode
- Holes drilled per micron of coating thickness was used to compare coatings
- Coatings provided 2.5x wear life of uncoated end mills in machining AISI 316SS

Machining with AlCr-Oxinitride PVD Coated Cutting Tools

A. Pilkington^{*ab}, S.J. Dowey^{abc}, J.T. Toton^{ab} and E.D. Doyle^{ab}

^a Department of Physics, School of Applied Sciences, RMIT University, Swanston Street, Melbourne, VIC 3000, Australia

^b Defence Materials Technology Centre, Level 2 No.24 Wakefield Street, Hawthorn, VIC 3122, Australia

^c Sutton Tools Pty Ltd, 378 Settlement Road, Thomastown, VIC 3074, Australia

*Corresponding author: antony.pilkington@rmit.edu.au

keywords: tool wear, drilling, milling, PVD, oxi-nitride coating, cathodic arc, AlCrN

Abstract

Physical Vapour Deposition (PVD) coating materials based on transition metal oxynitrides have been found to offer improved oxidation resistance for tooling applications. Arc deposited $\text{AlCrO}_x\text{N}_{1-x}$ coatings were tested on M2 HSS drills by drilling 2.5D holes in AISI D2. At a speed of 30 m/min and feed 0.025 mm/rev the mean tool life was 17.2 holes / μm for coatings made with a N_2/O_2 ratio of 0.9/0.1. Coating deposition with a pulse bias of 10 kHz was found to improve tool life in the drilling test by 10% compared to DC bias coatings. In milling of stainless steel $\text{AlCrO}_x\text{N}_{1-x}$ coated carbide end mills cutting AISI 316 at 70 m/min achieved a cut length 2.5X uncoated tools under the accelerated test conditions.

1. Introduction

The surface design of metal cutting tools for increased performance has presented tribologically challenging demands for the design of Physical Vapour Deposition (PVD) coatings. A combination of high temperature oxidation resistance, toughness and resistance to both chemical and abrasive wear processes is required [1, 2] and conventional ceramic thin film coatings based on transition metal nitrides or carbides,

1 such as TiN, CrN or TiCN [3, 4], have proved inadequate as cutting speeds are
2 increased or difficult to machine materials are encountered [5]. Improved wear
3 resistance with high hardness has been achieved by alloying of Al with Ti or Cr to
4 provide TiAlN or CrAlN coatings with the capability to form a protective aluminium
5 oxide in thermally activated tribocontacts [6]. The AlCrN coatings with ~70 at% have
6 been found to provide oxidation resistance to higher temperatures of ~900 °C than
7 the AlTiN coatings with similar Al content [7, 8] and the appearance of AlN
8 (hexagonal) in the phase composition is delayed until higher temperatures.
9

10 These ternary nitride coatings provided tougher fine grained coating layers through a
11 nanocomposite structure or nano-layered architectures [9, 10]. Both TiAlN and AlCrN
12 have been successfully deposited and commercialised through sputtering [11],
13 cathodic arc [12, 13] and evaporation [14] PVD technologies. The hot hardness and
14 diffusion barrier layer properties of Al_2O_3 [15-17] are attractive for tooling
15 applications. However many technological and thermodynamic obstacles exist for
16 the PVD of alumina coatings, with meta-stable phases presenting potential
17 weaknesses through transformation in metal cutting applications [18-20]. In contrast
18 alumina deposited by Chemical Vapour Deposition (CVD) has been extensively
19 developed but remains unsuitable for the coating of engineering tooling
20 manufactured from high speed steels (HSS) due to the process temperature of ~900-
21 1000 °C [21] [22] [23]. Therefore other routes to improving the oxidation resistance of
22 TiAlN and AlCrN have been investigated e.g. by intentionally doping AlCrN ceramic
23 coatings with various elements, such as Si [24], including Al_2O_3 as a minority phase
24 in a quaternary composition by O_2 addition [25] or by including thin intermediate
25 diffusion barrier layers of TiN [26] or Al_2O_3 in a multilayer coating [27]. The properties
26 of sputtered AlCr-O-N coatings have been shown to be dependent on both the Al-Cr
27
28
29
30
31
32
33
34
35
36
37
38
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60
61
62
63
64
65

ratio and proportion of O₂ incorporated [24, 28, 29]. Three types of sputtered AlCr-oxinitride have been identified; at high N₂ compositions >78% the FCC CrN structure is retained and the coatings have high hardness. Oxygen rich compositions exhibit a corundum type structure with medium-high hardness. Intermediate phase compositions had lower hardness which may include some amorphous material [16]. Barthelmä [30] showed that a series of arc deposited AlCr_xO_yN_z coatings had a microhardness maxima of 55 GPa for 10 At% O₂ content which was higher than comparative AlCrN coatings (20 GPa). Najafi [31] prepared a series of AlCr(O_xN_{1-x}) coatings at 550 °C using medium frequency pulse bias (-35 V) and AlCr cathodes in a Lateral Rotating Arc process with various O₂ /N₂ ratios. Low O₂ content coatings (x<0.6) had high hardness ~ 30-33 GPa and fcc structure, coatings made with intermediate O₂ content (0.6<x<0.97) had lower hardness of 26 GPa and coatings with x>0.97 had a phase composition of α-(Al,Cr)₂O₃ with increased hardness of 28 GPa. The AlCr-oxinitrides with intermediate O₂ content were metastable and on heating to 1000 C in Ar transformed to a mixed phase composition of (Al,Cr)₂O₃ (in corundum structure) and fcc AlCrN.

In this work N₂ rich AlCrO_xN_{1-x} arc deposited coatings were prepared at 480 -500 °C with DC and pulse unipolar bias. Machining studies were carried out to investigate the wear protection properties of coatings in a drilling test machining AISI D2 with HSS drills and in milling of AISI 316 stainless steel with carbide end mills. A comparison with commercial AlCrN arc deposited coatings was made and the suitability of AlCrN as an interface layer to prevent oxidation of the HSS during processing was assessed.

2. Experimental

1 A series of $\text{AlCrO}_x\text{N}_{1-x}$ coatings were deposited in an industrial capacity cathodic arc
2 PVD system (Balzers Innova) according to a two factor two level experimental
3 design. The factors investigated were the reactive gas N_2/O_2 ratio with 2 levels of
4 0.9/0.1 and 0.75/0.25, and the negative bias mode with the levels set to either DC
5 (level +1) or pulse unipolar with a frequency of 10 KHz (level -1). The bias level was
6 maintained at an average value of -80V for both bias modes. Substrates were
7 preheated to 450 °C and cleaned in-situ by Ar ion etching at 2×10^{-2} mbar for 30
8 minutes prior to coating deposition. The coating temperature was maintained at 480-
9 500 °C which permitted the coating of both HSS and WC substrates in the same
10 batch. The reactive gas pressure was maintained constant at 2.5×10^{-2} mbar. The
11 cathodes (targets) used had an Al:Cr composition of 70:30 at% and purity 99.95%.
12 The evaporators were operated with DC current in steered arc mode in order to
13 maintain low macroparticle emission, which is well known to affect both the surface
14 texture and morphology of cathodic arc PVD coatings [32-36]. The coating
15 architecture adopted consisted of 3 layers, an AlCrN bonding and functional layer of
16 1.5-2 μm thickness, a 100 nm transition layer with a linear variation of non-metal
17 content from nitride to oxinitride with a composition controlled by the reactive gas
18 volumetric flow rates. The toplayer of $\text{AlCrO}_x\text{N}_{1-x}$ was then deposited to achieve an
19 overall thickness in the range of 4-4.5 μm . The deposition parameters are
20 summarised in Table 1.

21 The series of 4 $\text{AlCrO}_x\text{N}_{1-x}$ coatings were deposited onto polished 6 x 1 mm thick
22 WC-10 wt% Co blades for characterisation studies. A Hysitron Ti950 Triboindenter
23 equipped with a Berkovich indenter tip was used to measure the surface hardness
24 and reduced modulus of the coatings. Indents were made on a 7x7 grid with 20 μm
25 spacing under a series of loads from 1-3 mN. Analysis of the force-indentation depth
26

1 data was carried out with TriboScan v.9 software according to the methodology
2 reported in ref. [37] incorporating the area function of the indenter tip.
3

4 Two types of engineering tooling were coated with $\text{AlCrO}_x\text{N}_{1-x}$ for wear and
5 performance evaluation in drilling and end milling. Commercial quality 6.35 mm
6 (0.25") diameter AISI M2 HSS jobber drills were used for drilling trials. The drills
7 were prepared by walnut shell blasting to remove edge burrs followed by a drag
8 polishing process in abrasive media to radius the cutting edges and remove surface
9 grinding damage. Fig. 1 shows the lip condition of a typical drill after this procedure.
10 Edge burrs have been removed but the tool geometry and grinding surface texture
11 were not significantly affected. Sets of 9 drills per coating group were randomly
12 selected to enable statistical analysis of test results. A 50 mm thick 12% Cr 1.5% C
13 cold work tool steel plate (Cryodur 2379 [38] composition equivalent to AISI D2) in
14 the annealed condition was used as the workpiece. The plate was prepared by face
15 milling to 1 mm depth to remove the heat treatment scale from the surface. The
16 workpiece hardness and adhesive properties greatly affect the tribological couple of
17 drill cutting edge and chip contact, therefore the plate surface hardness and
18 uniformity was investigated prior to the drill test with a Leeb D TIME GROUP TH107
19 rebound portable hardness tester. The surface hardness survey returned an average
20 hardness of 515.1 HLD (approximately 235 HB) with a Std. Dev. of 15.2 HLD.
21 Appropriate cutting conditions for the experimental test were established by drilling
22 the plate with commercial AlCrN coated test drills at various speeds in the range of
23 30-40 m/min. Cutting parameters of 30 m/min and a feed of 0.125 mm/rev achieved
24 a mean drill life of 40-50 holes with this set of test drills. These parameters were
25 adopted for the testing of the $\text{AlCrO}_x\text{N}_{1-x}$ coated drills. Blind holes were drilled in a
26 randomised array to a depth of 2.5 diameters (15.87 mm) on a HAAS VF2 CNC
27
28
29
30
31
32
33
34
35
36
37
38
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60
61
62
63
64
65

1 machining centre with a flood coolant emulsion (Hocut 960) at a concentration of 7-
2 8%. The parameters represented an accelerated life test with failure criteria
3 determined by an audible screech. A group of the prepared test drills were
4 commercially coated with AlCrN by a cathodic arc process and included in the study
5 for comparison as a state of the art high performance PVD coating.
6
7
8
9
10

11 An accelerated performance study of coated carbide tooling was carried out by end
12 milling of AISI 316L austenitic stainless steel in a HAAS VF Super 2 CNC machining
13 centre. Carbide end mills of type E535-4mm Harmony vary-helix R35/38 were
14 selected [39]. This tool had design features appropriate to high performance
15 applications including edge preparation, increased corner strength provided by a 45°
16 chamfer and chatter resistance due to the vary helix. High edge toughness was
17 provided by the sub-micron alloy carbide grade. The end mills were used in 3
18 surface conditions: uncoated (UC), coated with the 4 different AlCrO_xN_{1-x} coatings
19 and a further set were coated with a commercial AlCrN coating similar to that used in
20 the drill tests. Climb milling was carried out with a radial depth of cut $a_e=0.3D$ (1.2
21 mm), axial depth of cut $a_p=1D$ (4mm), speed $V=70$ m/min and a feed per tooth of
22 $f_z=0.022$ mm. The stainless steel workpiece in the form of a 50mm square bar was
23 supplied in the annealed condition. The mill finish was faced off from all surfaces
24 prior to testing and the surface hardness was 267 HV30 with a Std. Dev. of 3 HV30.
25 Minimum quantity lubrication (MQL) was used with a mist of Unist Coolube 2210.
26 This was introduced into the cut by a compressed air stream at a dose rate of
27 approximately 0.086 ml/m of cut length. Cutting force data for F_x , F_y and F_z was
28 collected during machining of shorter 50 mm sections of the workpiece mounted on a
29 Kistler 9257B 3 component dynamometer table. The dynamometer signals were
30 input to Kistler 5011 charge amplifiers and converted to voltage signals, which were
31
32
33
34
35
36
37
38
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60
61
62
63
64
65

then routed through a Daqbook 200A multichannel analogue to digital converter with the sampling frequency set to 500 Hz. The digital data was acquired and analysed using DaqView v7-13-14 software.

An Alicona Infinite Focus Microscope (IFM) was used to observe the wear progression of both drills and end mills. One drill from each coating run was imaged after drilling groups of 10 holes until failure. The corner wear V_b of the end mills was measured from IFM images using the Alicona IFM 3.5 software tools after each 12m cut. The coating thickness on the drill and end mill lands was measured from SEM images made on polished transverse cross sections prepared from unworn sections of tools after completion of the machining tests.

3. Results and discussion

3.1 Coating thickness, morphology and mechanical properties

The coating thickness measurements in Table 1 indicated that the $\text{AlCrO}_x\text{N}_{1-x}$ coatings had a thickness in the range of 4.4 -4.78 μm on drills and slightly greater thickness of 4.78 -5.29 μm on the end mills. The difference in coating thickness between end mills and drills may be attributed to differences in the jig masking during coating deposition. The $\text{AlCrO}_x\text{N}_{1-x}$ coated drill groups had similar coating thickness; however the commercially coated tools had lower coating thicknesses of 2 μm on the drill lands and 2.6 μm on the end mills.

Fig. 2 shows SEM images of fracture cross sections of the $\text{AlCrO}_x\text{N}_{1-x}$ coatings on WC. A feature of the cross sections was that the AlCrN base layer had excellent adhesion to the WC substrate and all coatings had a compact morphology without evidence of columnar growth. No delamination was evident at the interface between the AlCrN and $\text{AlCrO}_x\text{N}_{1-x}$ layers in the coatings examined. This confirmed that the transition layer provided effective bonding as the ceramic film composition was

varied from nitride to oxi-nitride. A difference in the topography of the fracture surface was observed between the DC coatings shown in Figs. 2(a) (c) and pulse bias coatings shown in Figs. 2(b) (d). The DC bias coatings exhibited a more granular or faceted fracture, similar to that evident in the AlCrN base layers, whereas the pulse bias coatings of Run 3 and Run 4 featured a smoother fracture cross section. The addition of O₂ during the deposition of the AlCrO_xN_{1-x} toplayer had an adverse effect on the surface roughness in comparison to the commercial AlCrN coatings. The AlCrO_xN_{1-x} coatings featured a greater number of larger ~2 -10 μm diameter surface macroparticles. It was evident that the macroparticles introduced morphological defects into the AlCrO_xN_{1-x} coating layers with an indication from surveys of larger areas of the SEM images that the macroparticle incorporation gradually increased after the transition layer was formed. This was indicative of a gradual poisoning effect of O₂ on the AlCr target surface with the growth of oxide nodules. Fig. 3 shows an example of the appearance of an O₂ poisoned target face after run 3. Investigation of non-conductive oxide nodules on a cathode by IFM indicated step heights of 500 -800 nm and characteristic diameters of 0.5 -1 mm. It is therefore probable that these nodules acted as both physical and dielectric barriers for the movement of arc spots and may hinder arc splitting. The effect on macroparticle emission is opposite to the type 1 (contaminated surface) arc discharges operating in Ar +O₂ described in [40] which reported greater arc spot speed for cathodic arcs operated with O₂. Both increased current density and reduced arc spot mobility are well known to promote the appearance of larger diameter macroparticles in the arc evaporated material flux [3, 41] and additions of Si to the AlCr cathode composition have been proposed recently to address this issue or through the use of pulsed arc current by Ramm [42].

The surface texture of the $\text{AlCrO}_x\text{N}_{1-x}$ coatings caused some difficulties for the nanoindentation investigation and it was necessary to polish the sample surface using 3 μm diamond compound in order to achieve reliable nanoindentation results. Table 2 shows data of the coating hardness and reduced modulus which is plotted in Fig. 4 where it is clear that the series of coatings formed 2 groups based on the H and E' values. Coatings from runs 1 and 3 made using a N_2/O_2 ratio of 0.75 /0.25 had lower H values in the range of 24.6 -24.8 GPa. The coatings made using lower O_2 contents (N_2/O_2 ratio 0.9 /0.1) had a higher hardness of 32 GPa. which was comparable to the commercial AlCrN coating.

Fig. 5(a) shows the interaction plot of the hardness values for the $\text{AlCrO}_x\text{N}_{1-x}$ groups. No dependence on the bias mode is evident at the lower O_2 level whereas a small effect is shown at the higher O_2 level of 0.25. The effect of the O_2 content on H is significant, shown in the lower left panel of Fig. 5(b). None of these coatings can be classed as “super hard” [43] and had a lower hardness than the 44 -55 GPa reported in [30] for arc deposited AlCrON coatings. The reduced modulus E' values showed a more complex relationship than for the hardness. The commercial AlCrN coating had the largest value of E' of 382.8 GPa. The lower O_2 content coatings had intermediate values of 332-337 GPa whereas the high O_2 content coatings had the lowest E' values of 262-285 GPa. in Fig. 5(b) there is a small dependency of E' on bias mode since both pulse bias coatings had greater E' than the DC values for the two different O_2 contents. However some caution in interpretation is necessary due to the difficulties inherent in obtaining reliable indents from arc deposited coatings, indicated by the standard deviation in the E' value (in Table 2) for the Run 3 coating. The toughness of PVD coatings may be characterised by the H/E relationship [44] which is a measure of the elastic deformation capacity of a coating and is important

in metalworking where the tool is subject to cyclic impact loading. The H/E' ratios calculated from the experimental values of H and E' of the $AlCrO_xN_{1-x}$ coatings fall in a range of 0.087 to 0.98 which indicated that these coatings may be expected to show similar toughness to the commercial AlCrN coating.

3.2 Drilling of D2 Tool Steel Plate

The number of holes drilled to failure by the coating groups is presented as a boxplot in Fig. 6(a). The plot indicates the data range, median number of drilled holes and the 25% and 75% quartile positions. The average number of holes drilled ranged from 36 to 80 across the drill groups. The median values for the $AlCrO_xN_{1-x}$ coatings showed a trend of increasing number of holes with decreasing O_2 content in the range 0.25 to 0.1. Comparing the data groups by bias level it is clear that the pulse bias increased the average drill life in comparison to the DC case for both the higher O_2 level (runs 1 and 3) and also for the lower O_2 level. However the data groups overlap for the coatings made with a N_2/O_2 ratio of 0.9 /0.1 and the difference in tool life is therefore not statistically significant. The group of drills coated with 2 μm of AlCrN showed the lowest median number of holes drilled and also the lowest variance. It is well known that coating thickness has a significant effect on the drill life therefore the data was normalised according to the average coating thickness for each group (Fig. 6(b)). The AlCrN coated drills showed the highest mean number of holes per μm at 17.8. The pulse bias $AlCrO_xN_{1-x}$ coating with a N_2/O_2 ratio of 0.9 /0.1 had wear resistant properties similar to the commercial AlCrN coating with 17.2 holes per μm under these test conditions. Fig. 6(c) shows that both O_2 level and bias level have an effect on the number of holes drilled per micron. The effect of bias is greater at the higher O_2 level and the effect of O_2 level is greater for the DC bias coatings.

The lip wear for an AlCrN coated drill after 30 holes is shown in the IFM image in Fig. 7(a). This group had the lowest average number of holes drilled. A 20 μm wide wear land can be seen linking the worn corner to the chisel point. The negative rake of the chisel to the drill centre has been completely worn away so that the chisel point behaves as a semi-conical indenter. The rake face at the outer corner shows the formation of a wear land which together with the severe blunting of the chisel edge indicates imminent drill failure, which occurred at 36 holes for the drill imaged. Fig. 7(b) shows a drill from R4 (10 kHz N_2/O_2 0.9 /0.1) which exhibited lower wear than the AlCrN coated drill. The lip wear again appeared uniform and the wear process is mainly abrasive wear since the wear land did not show oxidation discolouration and workpiece adhesion was minimal. This drill showed the appearance of an outer wear facet on the rake face after 60 holes, evident in Fig. 7(c) but continued to drill a total of 80 holes. The thicker PVD coating on the $\text{AlCrO}_x\text{N}_{1-x}$ drills from Run 4 together with the high hardness of 32 GPa provided abrasive wear resistance against the hard chromium carbides present in the workpiece [45] and a degree of thermal protection which enabled the greater number of holes to be drilled.

It was observed that the average performance of the various treatments in holes/ μm closely followed the trend in hardness values (Table 2) and also E, as the H/E ratio was nominally similar.

3.3 End milling of austenitic stainless steel AISI 316L

The progression of corner wear V_b with cut length is shown in Fig. 8. The cut length achieved by the uncoated end mill was 6.9 m whereas the coated tools all cut more than 24 m. The general trend of the corner wear showed a high initial rate (wear-in phase) which then stabilised at a lower rate (steady state wear) after 5 m. The test data did not include a wear out phase, except for the AlCrN coated tool. The

1 accelerated conditions eventually caused tool failure by shank fracture at the flute
2 run out rather than by edge wear or chipping of the margins. Lubrication of the
3 cutting process by the MQL oil mist was adequate and no thermally decomposed oil
4 residue was apparent on the end mills. The greatest wear rate V_b was shown by the
5 uncoated end mill and the wear of $\text{AlCrO}_x\text{N}_{1-x}$ coatings from runs 3-4-5 showed a
6 similar V_b at 5 m cut length. However, the commercial AlCrN coating and the
7 $\text{AlCrO}_x\text{N}_{1-x}$ coating from run 1 showed lower values of V_b for the DC N_2/O_2 ratio 0.75
8 /0.25 coating from run 1. A discussion of the milling results in terms of the measured
9 mechanical properties of the coatings is more complex than for the drilling test. The
10 end mills coated in run 1 and run 3 with the same N_2/O_2 ratio of 0.75 /0.25 have
11 similar hardness values of 24-25 GPa and similar thickness values of 4.4-4.8 μm but
12 showed an opposite response of V_b with cut length, representing the lowest and
13 highest values from the $\text{AlCrO}_x\text{N}_{1-x}$ coated tooling respectively. This outcome is
14 opposite to the performance of the run 1 coatings in the drilling test where the
15 coatings from run 1 produced the lowest number of holes per micron. The
16 performance of the run 1 coating in this end milling test merits further investigation.
17 In milling the lower E' value measured for this coating may have provided an
18 advantage under the repetitive impact loadings applied to the end mill tooth as the
19 cut commences.

20
21
22
23
24
25
26
27
28
29
30
31
32
33
34
35
36
37
38
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60
61
62
63
64
65
Plots of cutting forces against data point for uncoated (UC) and coated tools are
presented in Figs. 9(a)-(f) respectively. The force F_x in the direction of table feed
showed peaks typical of climb milling at the entry and exit of the cut. The magnitude
of the F_y forces (normal reaction force) was approximately 3x greater than the F_x
values. The uncoated tool and coated tools showed a different response in cutting
forces as wear of the corner and margins increased. Fig. 10 shows the change in

average F_y for the end mills after 5 m cut length (UC) and 24m (coated tools). The average forces of the uncoated tool were initially 143 -155 N but increased by 49% to 215 N after a cut length of 5m. In Fig 9(a) the peaks in F_y are 250 N for the worn tool, which was attributed to the 100 μm margin creating a larger impact force on entering the workpiece. The coatings made at an N_2/O_2 ratio of 0.75 /0.25 showed a lower average F_y than coatings made at 0.9 /0.25, which may indicate lower adhesive forces between chip and rake face. The AlCrN coating had an initial F_y of 143 N which was intermediate between runs 1 and 3 (higher O_2 coatings) and that of runs 4 and 5. Run 1 showed no change in the average F_y and this is consistent with the low corner wear shown in Fig. 8. The F_y values in fig. 10 can be partly explained by the edge radii measured on the unused tools. Fig. 11 shows that the UC, AlCrN and lower O_2 coatings had a linear relationship for F_y with edge radius and these coated tools show an edge radius approximately equal to the uncoated tool plus the AlCrN or $\text{AlCrO}_x\text{N}_{1-x}$ coating thickness. The $\text{AlCrO}_x\text{N}_{1-x}$ coatings made with higher O_2 ratio do not follow the radius- F_y relationship and this suggests that the lower F_y is due to tribological properties and the DC 0.75 N_2 0.25 O_2 may behave as a solid lubricant in this particular workpiece-coating-MQL system.

IFM images of the end mill margins are shown in Fig. 12. In Fig. 12(a) the UC tool is seen to have the lowest initial edge radius and was therefore the sharpest tool but had greater flank wear (Fig. 12(b)) and corner recession. The AlCrN coated tool had low wear of both rake and flank and in Fig. 12(d) the hard coating can be seen as a step close to the margin. The DC 0.75 N_2 0.25 O_2 coating showed wear of the $\text{AlCrO}_x\text{N}_{1-x}$ layer from an early stage yet still had an adherent AlCrN base layer and the lowest exposed carbide of the tools after 24m cut length, Fig. 12(e). The coatings in Figs. 12(f) to (h) showed wear of the $\text{AlCrO}_x\text{N}_{1-x}$ layer on the flank intermediate

1 between run 1 and the AlCrN tool. of the Adhesion of the AISI 316 was evident only
2 on the edges of the DC 0.9 N₂ 0.1 O₂ tool in Fig. 12(g).
3

4 Austenitic stainless steel is well known to promote adhesive wear and subject the
5 tool cutting edges to high stress due to work hardening from prior cuts together
6 together with high temperatures in zone 2 of the secondary shear zone [46-48]. The
7 wear mechanism of the UC tool was examined in detail in an SEM (Fig. 13(a)) where
8 the eccentric diametrical relief is at the left of the image and the rake face is on the
9 right. A wear land of 100 µm had developed with an adherent build up at the cutting
10 edge junction with the rake face and this material provided some protection for the
11 tool carbide material. The transient nature of this lamellar build up was indicated by
12 the detachment of a ribbon which showed a conformal boundary with the remaining
13 adherent layer. A detail of the cutting edge is shown in Fig. 13(b) where the chip flow
14 direction was from centre to bottom right down the rake face. The wear mechanism
15 of the uncoated tool is indicated by the evidence of adherent workpiece material on
16 the upper flanks of the grinding grooves and a step-like loss of carbide tool material
17 by micro fracture along some of the crests. The submicron grain size of the alloy
18 carbide was therefore beneficial in achieving a low wear rate since no edge
19 breakdown (notching) was observed and fracture was limited to a depth of the
20 nominal grain size. An SEM image of the AlCrN coated endmill is shown after 31 m
21 of cutting in Fig. 13(c). The worn cutting edge is different to that of the uncoated tool
22 and has retained a smooth radius with only ~10 µm of carbide exposed. Adherent
23 workpiece material is evident on the flank relief but is plate-like rather than
24 continuous. The AlCrN coating has been effective in preventing workpiece adhesion
25 along the rake to a depth of fz. In Fig. 13(d) wear of the AlCrON coating from run 4 is
26
27
28
29
30
31
32
33
34
35
36
37
38
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60
61
62
63
64
65

1 evident as a step on the rake face, however the area of worn carbide exposed is still
2 low despite the extent of the coating flank wear of 80 -100 μm .
3

4. Conclusions

4 $\text{AlCrO}_x\text{N}_{1-x}$ coatings deposited with an N_2/O_2 ratio of 0.9 /0.1 had hardness values of
5 32 GPa and were harder than coatings made with the N_2/O_2 ratio of 0.75 /0.25
6 which had hardness values of 24 GPa. A 2 μm adhesion layer of AlCrN was found to
7 be effective in preventing deterioration of the tool materials in the O_2 plasma
8 deposition process.
9

10 The average number of 2.5D blind holes drilled by $\text{AlCrO}_x\text{N}_{1-x}$ coated M2 jobber drills
11 in D2 tool steel was found to be related to the coating hardness. The coatings
12 deposited onto M2 HSS drills with a N_2/O_2 ratio of 0.9/0.1 performed better than
13 coatings made with the 0.75/0.25 N_2/O_2 ratio. Pulse bias coatings had a longer
14 lifetime than DC bias coatings for similar reactive gas deposition ratios. In the drilling
15 test the performance of the pulse bias 0.75/0.25 N_2/O_2 coating was 17.2 holes per
16 μm which was comparable to the commercial AlCrN coatings with 17.8 holes per μm .
17 Carbide end mills coated with $\text{AlCrO}_x\text{N}_{1-x}$ showed lower edge and corner wear than
18 uncoated tools in the machining of AISI 316 austenitic stainless steel and produced a
19 cut length greater than 24 m in the accelerated cutting test. The milling test showed
20 that the $\text{AlCrO}_x\text{N}_{1-x}$ coating made with DC bias at a N_2/O_2 ratio of 0.75/0.25 showed
21 the lowest corner wear in the milling test whereas this coating achieved the lowest
22 performance when drilling AISI D2 tool steel.
23

Acknowledgements

24 This body of work was undertaken by the DMTC with researchers from RMIT
25 University and Sutton Tools Pty. Ltd. The DMTC was established and is supported
26
27
28
29
30
31
32
33
34
35
36
37
38
39
40
41
42
43
44
45
46
47
48
49
50

by the Australian Government's Defence Future Capability Technology Centre (DFCTC) initiative.

The industrial DMTC partner Sutton Tools Pty. Ltd. provided sponsorship, tooling, research materials, coating deposition and access to the CNC machining laboratory of the Advanced Surface Solutions Facility (ASSF). The technical assistance of J. Phung of Sutton Tools Pty. Ltd. in carrying out the machining experiments is gratefully acknowledged.

The authors acknowledge the facilities, and the scientific and technical assistance, of the Australian Microscopy & Microanalysis Research Facility at the RMIT Microscopy & Microanalysis Facility, at RMIT University. The authors express their thanks to A. Pagon of RMIT Applied Physics for providing assistance and expertise in carrying out the nanoindentation investigations.

1. Holleck, H., *Materials selection for hard coatings*. J. Vac. Sci. Technol. A, 1986. **4**(6): p. 2661-2669.
2. Hogmark, S., Jacobson, S., Larsson, M., *Design and evaluation of tribological coatings*. Wear, 1999. **246**: p. 20-33.
3. Boxman, R.L., Martin, P.J., ed. *Vacuum Arc Science and Technology: Fundamentals and Applications*. 1995, Noyes Publications: New Jersey.
4. Münz, W.-D., *Titanium aluminum nitride films: A new alternative to TiN coatings*. J. Vac. Sci. Technol. A, 1986. **4**(6): p. 2717-2726.
5. Fox-Rabinovich, G.S., Kovalev A.I., Aguirre M.H., Beake B.D., Yamamoto, K., Veldhuis, S.C., Endrino, J.L., Wainstein, D.L., Rashkovskiy, A.Y., *Design and performance of AlTiN and TiAlCrN PVD coatings for machining of hard to cut materials*. Surface & Coatings Technology, 2009. **204**: p. 489–496.
6. Kawate, M., Hashimoto, A. K., Suzuki, T., *Oxidation resistance of $Cr_{1-x}Al_xN$ and $Ti_{1-x}Al_xN$ films*. Surface and Coatings Technology, 2003. **165**: p. 163-167.
7. Willmann, H., Mayrhofer, P. H., Hultman, L., Mitterer, C., *Hardness evolution of Al–Cr–N coatings under thermal load*. J. Mater. Res., 2008. **23**(11): p. 2880-2885.
8. Reiter, A.E., Derflinger, V.H., Hanselmann, B., Bachmann, T., Sartory, B., *Investigation of the properties of $Al_{1-x}Cr_xN$ coatings prepared by cathodic arc evaporation*. Surface & Coatings Technology, 2005. **200**: p. 2114– 2122.
9. Stueber, M., Holleck, H., Leiste, H., Seemann, K., Ulrich, S., Ziebert, C., *Concepts for the design of advanced nanoscale PVD multilayer protective thin films*. Journal of Alloys and Compounds, 2009. **483**: p. 321-333.

10. Yashar, P.C., Sproul, W.D., *Nanometer scale multilayered hard coatings*. Vacuum, 1999. **55**: p. 179-190.
11. Erkens, G., Cremer, R., Hamoudi, T., Bouzakis, K.-D., Mirisidis, I., Hadjiyiannis, S., Skordaris, G., Asimakopoulos, A., Kombogiannis, S., Anastopoulos, J., Efstathiou, K., *Properties and performance of high aluminum containing (Ti,Al)N based supernitride coatings in innovative cutting applications*. Surface & Coatings Technology, 2004. **177–178** p. 727-734.
12. Endrino, J.L., Fox-Rabinovich, G.S., Gey, C., *Hard AlTiN, AlCrN PVD coatings for machining of austenitic stainless steel*. Surface & Coatings Technology, 2006. **200**: p. 6840–6845.
13. Kalss, W., Reiter, A., Derflinger, V., Gey, C., Endrino, J.L., *Modern coatings in high performance cutting applications*. International Journal of Refractory Metals & Hard Materials, 2006. **24**: p. 399-404.
14. Wang, L., Nie, X., Housden, J., Spain, E., Jiang, J.C., Meleti. E.I., Leyland, A., Matthews, A., *Material transfer phenomena and failure mechanisms of a nanostructured Cr–Al–N coating in laboratory wear tests and an industrial punch tool application*. Surface & Coatings Technology, 2008. **203**: p. 816-821.
15. Ashenford, D.E., Long, F., Hagston, W. E., Lunn, B., Matthews, A. , *Experimental and theoretical studies of the low-temperature growth of chromia and alumina*. Surface & Coatings Technology, 1999. **116-119**: p. 699-704.
16. J.M. Schneider, W.D.S., A. Matthews. , *Phase formation and mechanical properties of alumina coatings prepared at substrate temperatures less than 500°C by ionized and conventional sputtering*. . Surface & Coatings Technology, 1997. **94-95**: p. 179-183.
17. Musil, J., Blažek, J. , Zemana, P., Proksťová, S., Šasťek, M., Čerstvý, R. , *Thermal stability of alumina thin films containing γ -Al₂O₃ phase prepared by reactive magnetron sputtering*. App. Surface Science, 2010. **257**: p. 1058-1062.
18. Carter, D., McDonough, G., *Enhanced reactively sputtered Al₂O₃ deposition by addition of activated reactive oxygen*, in SVC 42nd Annual technical Conference. 1999 Society of Vacuum Coaters: Chicago, IL, USA. p. 1-8.
19. Andersson, J.M., *Low-temperature growth of alumina*, in *Thin Film Physics Division, Department of Physics and Measurement Technology*. 2004, Linköping University: SE-581 83 Linköping, Sweden. p. 70.
20. Dragoo, A.L., Diamond, J.J., *Transitions in vapor deposited alumina from 300 to 1200 C*. J. Am. Ceram. Soc., 1967. **50**(11): p. 568-574.
21. Schintlmeister, W., Wallgram, W., Kanz, J., *Properties, applications and manufacture of wear resistant hard material coatings for tools*. Thin Solid Films, 1983. **107**: p. 117-127.
22. Ruppi, S., *Deposition, microstructure and properties of texture controlled CVD α -Al₂O₃ coatings*. Int. J. Refractory metals and Hard Materials., 2005. **23**: p. 306-316.
23. Laimer, J., Fink, M., Mitterer, C., Stořri, H., *Plasma CVD of alumina—Unsolved problems*. Vacuum, 2005. **80**: p. 141-145.
24. Karimi, A., Morstein, M., Cselle, T., *Influence of oxygen content on structure and properties of multi-element AlCrSiON oxynitride thin films*. Surface & Coatings Technology, 2010. **204**: p. 2716-2722.

25. Leyendecker, T., Rass, I., Erkens, G., Feldhege, M., *TiAlN-Al₂O₃ PVD-multilayer for metal cutting operation*. Surface and Coatings Technology, 1997. **97**(1-3): p. 790-793.
26. Endrino, J.L., Fox-Rabinovich, G.S., Reiter, A., Veldhuis, S.V., Galindo, R.E., *Oxidation tuning in AlCrN coatings*. Surface & Coatings Technology, 2007. **201**: p. 4505-4511.
27. Schier, V., Doerwald, D., *Break thorough in PVD coated aluminium oxide*. Hauzer For You, 2005(10): p. 3-4.
28. Stueber, M., Diechle, D., Leiste, H., Ulrich, S., *Synthesis of Al-Cr-O-N thin films in corundum and f.c.c. structure by reactive r.f. magnetron sputtering*. Thin Solid Films 2011. **519**: p. 4025-4031.
29. Stüber, M., Albers, U., Leiste, H., Seemann, K., Ziebert, C., Ulrich, S., *Magnetron sputtering of hard Cr-Al-N-O thin films*. Surface & Coatings Technology, 2008. **203**: p. 661-665.
30. Barthelmä, F., Frank, H., Mahr, P., Reich, S., *Oxygen-improved hard coatings for high performance cutting processes*. Procedia CIRP, 2012. **1**: p. 208 - 213.
31. Najafi, H., Karimi, A., Dessarzin, P., Morstein, M., *Correlation between anionic substitution and structural properties in AlCr(O_xN_{1-x}) coatings deposited by lateral rotating cathode arc PVD*. Thin Solid Films, 2011. **520**: p. 1597-1602.
32. Anders, A., *Approaches to rid cathodic arc plasmas of macro and nanoparticles: a review*. Surface & Coatings Technology, 1999. **120-121**: p. 319-330.
33. Ellrodt, M., & Kühn, M., *Investigations of the cathode spot dynamics in a vacuum arc coating process*. Contributions to Plasma Physics, 1996. **36**(6): p. 687-696.
34. B"uschel, M., Grimm, W., *Influence of the pulsing of the current of a vacuum arc on rate and droplets*. Surface & Coatings Technology, 2001. **142-144**: p. 665-668.
35. Ehasarian, A.P., Hovsepian, P.Eh., New, R., Valter, J., *Influence of steering magnetic field on the time resolved plasma chemistry in cathodic arc discharges*. Journal of Physics D: Applied Physics, 2004. **37**(15): p. 521-524.
36. Harris, S.G., Doyle, E.D., Wong, Y.-C., Munroe, P.R., Cairney, J.M., Long, J.M., *Reducing the macroparticle content of cathodic arc evaporated TiN coatings*. Surface & Coatings Technology, 2004. **183**: p. 283-294.
37. Pharr, G.M., Oliver, W.C., *Measurement of thin film mechanical properties using nanoindentation*. MRS Bulletin, 1992(July): p. 28-33.
38. *Cryodur® 2379 Technical Data Sheet*. 2012, Smolz + Bickenbach.
39. Sutton Tools Pty Ltd., http://www.sutton.com.au/assets/515/1/499980315_HighPerformance_Catalogue_Aust_2011.pdf. 2011. p20.
40. Mustapha, N., Howson, R.P., *Comparison of unbalanced magnetron sputtering and filtered arc evaporation for the preparation of films onto insulating substrates*. Vacuum, 1998. **49**(2): p. 75-79.
41. Münz, W.-D., Smith, I.J., Lewis, D.B., Creasey, S., *Droplet formation on steel substrates during cathodic steered arc metal ion etching*. Vacuum, 1997. **48**(5): p. 473-481.
42. Ramm, J., Neels, A., Widrig, B., Döbeli, M., Vieira, L. d-A., Dommann, A., Rudigier, H., *Correlation between target surface and layer nucleation in the*

- 1 *synthesis of Al–Cr–O coatings deposited by reactive cathodic arc evaporation.*
2 Surface & Coatings Technology, 2010. **205**: p. 1356-1361.
- 3 43. Musil, J., *Hard and superhard nanocomposite coatings.* Surface & Coatings
4 Technology, 2000. **125**: p. 322-330.
- 5 44. Leyland, A., Matthews, A., *On the significance of the H/E ratio in wear control:*
6 *a nanocomposite coating approach to optimised tribological behaviour.* Wear,
7 2000. **246**: p. 1-11.
- 8 45. Sandberg, O., Jönson, L. . *New generation of tool steels made by spray*
9 *forming.* in *Proceedings of the 6th International Tooling Conference.* 2002.
10 Karlstad.
- 11 46. Liew, W.Y.H., Ding, X., *Wear progression of carbide tool in low-speed end*
12 *milling of stainless steel.* Wear, 2008. **265**: p. 155-166.
- 13 47. Abou-El-Hossein, K.A., Yahya, Z. , *High-speed end-milling of AISI 304*
14 *stainless steels using new geometrically developed carbide inserts.* Journal of
15 Materials Processing Technology, 2005. **162-163**: p. 596-602.
- 16 48. Doyle, E.D., Horne, J.G., Tabor, D., *Frictional Interactions between chip and*
17 *rake face in continuous chip formation* Proc. R. Soc. Lond. A 1979. **366**: p.
18 173-183.
19
20
21
22
23
24
25
26
27
28
29
30
31
32
33
34
35
36
37
38
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60
61
62
63
64
65

Fig. 1. Uncoated 1/4" Dia. M2 HSS Jobber drill.

Fig. 2(a). Run 1 AlCrON DC 0.75 N2 0.25 O2.

Fig. 2(b) Run 3 AlCrON 10 KHz 0.75 N2 0.25 O2

Fig. 2(c) Run 5 AlCrON DC 0.9 N2 0.1 O2.

Fig. 2(d) Run 4 AlCrON 10 KHz 0.9 N2 0.1 O2.

Fig. 3. Oxide nodules on used AlCr 70:30 at% cathode.

Fig. 4. H-E' plot with 95% CI bars for AlCrOxNx-1 and AlCrN.

Fig. 5(a). Interaction plot for H.

Fig. 5(b). Interaction plot for E' .

Fig. 6(a). Boxplot of the number of holes drilled by coating.

Fig. 6(b). Boxplot of the number of holes drilled per micron.

Fig. 6(c). Interaction plot of O2 ratio and bias

Fig. 7(a). AlCrN coated drill after 30 holes.

Fig. 7(b). Run 4 10 kHz 0.9 N2 0.1 O2 drill lip after 30 holes.

Fig. 7(c). Run 4 drill lip after 60 holes.

Fig. 8. Plot of 4 mm end mill corner wear Vb machining AISI316L

Fig. 9(a). FxFy plot for UC end mill.

Fig. 9(b). FxFy plot for AlCrN end mill.

Fig. 9(c). FxFy plot Run 1 DC N2/O2 ratio 0.75/0.25.

Fig. 9(d). FxFy plot Run 3 10 kHz N2/O2 ratio 0.75/0.25

Fig. 9(e). FxFy plot Run 5 DC N2/O2 ratio 0.75/0.25.

Fig. 9(f). FxFy plot Run 4 10 kHz N2/O2 ratio 0.75/0.25.

Fig. 10. Average Fy at 0m and 5 m (UC) and 24m (coated tools).

Fig. 11. Edge radius in μm vs average F_y at cut 0.

Fig. 12(a). UC before use.

Fig. 12(b). UC after 5 m cut length.

Fig. 12(c). AlCrN as deposited.

Fig. 12(d). AICrN after 24 m cut length.

Fig. 12(e). Run 1 after 24m cut length.

Fig. 12(f). Run 3 after 24 m cut length.

Fig. 12(g). Run 5 after 24 m cut length.

Fig. 12(h). Run 4 after 24m cut length.

Fig. 13(a). Margin of uncoated endmill after 6.9m cut length.

Fig. 13(b). Detail of UC endmill margin after 6.9 m cut length.

Fig. 13(c). AlCrN coated tool margin after 31.5 m cut length.

Fig. 13(d). Corner of Run 4 end mill after 36m cut length.

Table 1. Coating deposition parameters and layer thickness.

Table 1. Coating deposition parameters and layer thickness from tool lands.

Coating thickness data in µm											
Run	Bias	N ₂ ratio	O ₂ ratio	Pressu re 10 ⁻² mb	T °C	Drill land Average Thickne ss	Std dev	End mill land			
								Erro r of Mea n	Averag e thickne ss	Std dev	Erro r of Mea n
1	DC	0.7 5	0.2 5	2.5	50 0	4.43	0.3 0	0.10	5.02	0.0 9	0.02
3	Puls e 10kHz z	0.7 5	0.2 5	2.5	50 0	4.78	1.2 3	0.39	5.11	0.0 8	0.03
5	DC	0.9	0.1	2.5	50 0	4.57	0.2 6	0.08	4.78	0.2 2	0.07
4	Puls e 10kHz z	0.9	0.1	2.5	50 0	4.65	0.2 2	0.07	5.29	0.1 7	0.06
AlCr N	DC	1	0	3.5	48 0	2.02	0.0 4	0.02	2.62	0.3 0	0.08

Table 2. Nanoindentation hardness and modulus of coatings.

Table 2. Nanoindentation hardness and reduced modulus of PVD coated WC coupons.

Run	Bias /reactive gas	H GPa	SD GPa	CI GPa	Modulus E' GPa	SD GPa	CI GPa	H/E`	range +-
1	DC	24.57	2.77	0.853	262.50	17.21	5.296	0.094	0.005
3	0.75N ₂ 0.25 O ₂ 10kHz	24.80	4.75	1.411	285.78	39.84	11.831	0.087	0.009
5	DC	32.96	2.36	0.685	337.29	12.51	3.633	0.098	0.003
4	0.9N ₂ 0.1 O ₂ 10kHz	32.36	2.09	0.629	332.37	17.75	5.334	0.097	0.003
AlCrN	DC	32.63	2.51	0.571	382.86	20.53	4.659	0.085	0.003